

透明 KIBITON[®] PB-5900

March 3, 2009

材料規格：

特性 (Properties)	測試方法 (Test Method)	測試條件 (Test Condition)	單位 (Unit)	PB-5900
引張強度 Tensile Strength	ASTM D638	1/8", 6 mm/min	Kg/cm ²	420
彎曲強度 Flexural Strength	ASTM D790	1/4", 2.8 mm/min	Kg/cm ²	850
彎曲彈性率 Flexural Modulus	ASTM D790	1/4", 2.8 mm/min	Kg/cm ²	24000
IZOD 衝擊強度 Izod Impact Strength	ASTM D256 (Notched)	1/4", 23°C	Kg-cm/cm	2.2
流動係數 Melt Flow Index	ASTM D1238	200°C, 5Kg	g/10min	12.0
軟化點 Vicat Softening Temp	ASTM D1525	1/8", 50 /hr		94
濁度 Haze	ASTM D1003	1/8"	-	5
硬度 Hardness	Shore D	-	-	72

以上數據僅代表一般通用數據，不代表每一產品的規格值