



CHI MEI CORPORATION

59-1 SAN CHIA, JEN TE, TAINAN COUNTY, TAIWAN R.O.C. TEL: 886-6-266-5000, FAX: 886-6-266-5555-7

泛用級 TPE, KIBITON[®] PB-575

August 19, 2004 VIW

材料特性

| 特性(Properties) | 測試方法(Test Method) | 測試條件(Test Condition) | 單位(Unit) | PB-575 |
|-------------------------|-------------------|----------------------|----------|---------------------|
| 丁二烯/苯乙烯比例 BD/SM | ASTM D1416 | - | % | 60/40 |
| 揮發份 Volatile matter | ASTM D1416 | - | wt% | 0.6 |
| 灰份 Ash Content | ASTM D1416 | - | wt% | 0.2 |
| 加工含油量 Oil Content | ASTM D1416 | - | phr | 50 |
| 流動係數 Melt Flow Index | ASTM D1238 | 200 ,5Kg | g/10min | 6.0 |
| 流動係數 Melt Flow Index | ASTM D1238 | 190 ,5Kg | g/10min | 4.5 |
| 硬度 Hardness | ASTM D2240 | - | Shore A | 63 |
| 比重 Specific Gravity | ASTM D792 | 23 | - | 0.94 |
| 外觀 Appearance | - | - | - | 發泡顆粒 Foam Pellet |
| 包裝 Bale Weight | - | - | Kg | 20 |

以上數據僅代表一般通用數據，不代表每一產品的規格值

若有任何疑問請洽產品推廣課 06-2665000, 06-2663000